



- The flooring shall be Polyflor Acoustix Gallery fx PUR, as supplied by Polyflor Ltd of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 3.5mm thickness.
- It shall be heterogeneous in construction with a 0.5mm clear PVC wear layer.
- The flooring shall incorporate a specially formulated polyurethane reinforcement, to significantly reduce maintenance costs.



- In accordance with EN651, the in-use classification must be at least 23/33/42 as described in EN 685: ie domestic areas with intense use; commercial areas with heavy traffic; and general light industrial areas.
- When tested to EN ISO 140-8, the product should achieve an impact sound reduction of 19dB.
- With regards the EN 13893 test for slip resistance, the flooring shall be classified DS, making it suitable for use in areas which are predominantly dry, but with occasional wet spillage. When tested to DIN 51130, the flooring shall be classified as R10. For safety flooring with sustainable wet slip resistance, refer to the Polysafe ranges.
- In respect of flame spread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Cfl-S1, achieving the criteria EN ISO 9239-1 $\geq 4.5 \text{ kW/m}^2$ and the mandatory requirement of EN ISO 11925-2 pass.
- When tested to EN 423 (ASTM F 1303-99), the flooring should achieve excellent chemical resistance.
- In respect of light fastness, the flooring shall have been fully tested to EN 20105-B02 Method 3 as having a pass to ≥ 6 .
- The product must have been fully tested for abrasion resistance and meet the requirements of abrasion Group T, as defined in EN 649.
- In respect of residual indentation, the flooring shall have been fully tested to EN 433 as having a pass to $< 0.2 \text{ mm}$.
- When tested to ENV 13419 AgBB VOC test, the flooring shall have passed, giving a low result.
- The flooring must be available in 2.01 metre width, including a 0.01 metre selvage for on site trimming, to minimise the number of joints.
- The flooring will achieve a BRE Global Environmental A+ Rating ENP 415 in the Green Guide to Specification.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge see the Polyflor ESD product ranges.



- The supplier of the floorcovering must be in possession of a valid quality systems certificate showing compliance with ISO 9001.
- The supplier of the floorcovering must be in possession of a valid environmental certificate showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out, in accordance with the instruction in BS 8203 in the UK and other relevant national standards. The result should not exceed 75%RH, if using a hygrometer, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed as outlined by Polyflor.
- Suitable for use with underfloor heating up to 27°C. See Polyflor installation instructions for details.
- Installation must be carried out in accordance with BS 8203, other relevant national standards and the instructions of Polyflor.
- All joints must be welded.



- Polyflor Acoustix Gallery fx PUR is recommended for residential and commercial areas where sound insulation is an important requirement as well as being attractive, modern and easy to maintain. Such areas include domestic housing as well as specific healthcare and education areas, including corridors, classrooms and wards.



- At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality. For clarification and for information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com

Acoustix Gallery fx™

Acoustic vinyl flooring



PRODUCT SPECIFICATION

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK
 UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551
 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912
 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM
 WEBSITE: WWW.POLYFLOR.COM

*James Halstead*TM
 FLOORING



2011

POLYFLORTM
 COVERING THE WORLD