

Polyflor Trento Collection


Domestic Cushion Vinyl

Please note: that there are 3 different datasheets within this range. This is due to the thickness of the vinyl.

Range 1 - Data Information



Liberty Honey Oak
643M



Empire Square 901D



New York Grey 749L



New York Cream 346L



Liberty Oak 662M

Range 2 - Data Information



Ellis Distressed Oak
696M




Rockefeller Limestone
206S



Ellis Antique Oak
602M



Broadway Slate 900E



Rockefeller Stone
196S



Radio City Marble
126S

Polyflor Trento Collection

Domestic Cushion Vinyl

Range 3 - Data Information



Warm Oak 613M



Warm Oak 909D



Warm Oak 997L



Warm Oak 613M

Polyflor Trento Collection

Domestic Cushion Vinyl

Range 1



Emissions tested in accordance with DIBt-principles



Product Information

Usage classification	EN ISO 10874 EN 685		22
Wear layer	EN ISO 24340 EN 429		0,20 mm
Total thickness	EN ISO 24346 EN 428		2,80 mm
Total weight	EN ISO 23997 EN 430		1500 gr/m ²
Standard widths	EN ISO 24341 EN 426		2 - 3
Standard length	EN ISO 24341 EN 426		30m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Residual Indentation	EN ISO 24343-2 EN 433		≤ 0,35 mm
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10

Polyflor Trento Collection

Domestic Cushion Vinyl

Range 2



Product Information

Usage classification	EN ISO 10874 EN 685		22
Wear layer	EN ISO 24340 EN 429		0,20 mm
Total thickness	EN ISO 24346 EN 428		3,50 mm
Total weight	EN ISO 23997 EN 430		1740 gr/m ²
Standart widths	EN ISO 24341 EN 426		2 - 3
Standard length	EN ISO 24341 EN 426		25m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Thermal resistance	ISO 8302		0,040
Residual Indentation	EN ISO 24343-2 EN 433		≤ 0,35 mm
Impact sound	EN ISO 717/2		Δ Lw 17 dB
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10
Assessment of static electrical propensity	EN 1815		<2,0kV
Resistance to household chemicals	EN 423 ISO 26787		good

Polyflor Trento Collection

Domestic Cushion Vinyl

Range 3



Product Information

Usage classification	EN ISO 10874 EN 685		22
Wear layer	EN ISO 24340 EN 429		0,20 mm
Total thickness	EN ISO 24346 EN 428		4,00 mm
Total weight	EN ISO 23997 EN 430		2240 g/m ²
Standard widths	EN ISO 24341 EN 426		2 - 3 - 4m
Standard length	EN ISO 24341 EN 426		20m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Residual Indentation	EN ISO 24343-2 EN 433		≤ 0,35 mm
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R11
Resistance to household chemicals	EN 423 ISO 26787		good
Impact sound	EN ISO 717/2		Δ Lw 17 dB