SPECIFICATION







0.35mm



 $4m \times 25m = 100m^2$, $3m \times 25m = 75m^2$ $2m \times 25m = 50m^2$



1780g/m²



GENERAL PERFORMANCE

EN 653 EN ISO 26986









ACOUSTIC IMPACT SOUND REDUCTION

EN ISO 140-8 ≥19dB EN ISO 10140-3 ≥19dB



SLIP RESISTANCE

EN 13893 Class DS (dry condition) AS/NZS 4586 R10 **DIN 51130** R10



REACTION TO FIRE

LIGHT FASTNESS

EN 13501-1 Class Bfl-S1



RESISTANCE TO CHEMICALS EN 423 (ASTM F 1303-99) Excellent chemical resistance



ABRASION RESISTANCE

EN 649 Group T



INDENTATION - RESIDUAL

ISO 105-B02 (Method 3) ≥6

EN 433 / ISO 24343-1 < 0.2 mm



DIMENSIONAL STABILITY

EN 434 / EN ISO 23999 < 0.40%



FLEXIBILITY

EN 435 (Method A) / EN ISO 24344 Pass 20mm Ø



THERMAL RESISTANCE

Suitable for underfloor heating ISO 8302 0.0525 m² K/W



CASTOR CHAIR (continuous use) ISO 4918 Pass

Suitable for castor chairs



FURNITURE LEG

FN 424 Pass Type 2 foot



VOC EMISSIONS

Indoor Air Comfort GOLD - Approved AgBB - Very low emissions



ELECTRICAL BEHAVIOUR (body voltage)

EN 1815 ≤2kV Classified as 'antistatic'



HYGIENE

All Polyflor commercial sheet vinyl ranges provide a continuous, impervious and hygienic flooring solution which can be confidently cleaned in accordance with recommended maintenance procedures and approved maintenance products. The implementation of an effective cleaning regime is the most important defence against infection.



ENVIRONMENTALLY PREFERABLE FLOORING

Polyflor Secura achieves BRE Global A rating (Generic) in the Green Guide to Specification in major use areas such as education and healthcare. Generic EN 15804 Environmental Product Declaration (EPD) available on request. It is 100% recyclable. Recyclable via the Recofloor scheme. Visit www.polyflor.com/environment. Polyflor Secura features a high quality,

cross-linked polyurethane reinforcement, UV cured to provide a low cost, polish-free maintenance regime for the lifetime of the flooring.



Polyflor Secura is suitable for use in residential or commercial buildings where sound insulation is an important feature. For information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Customer Technical Support on +44 (0)161 767 1912, or email tech@polyflor.com.



WEBSITE: WWW.POLYFLOR.COM

For information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.

*For safety flooring with sustainable wet slip resistance, refer to the Polysafe ranges.

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM









Refer to the BRE Green Guide for more details

PERFORMANCE AND **PROPERTIES**

Recofloor[®]

In collaboration with the European Resilient Flooring Manufacturers' Institute (ERFMI), Polyflor Ltd supports sustainable construction via Environmental Product Declarations (EPDs)





