










TECHNICAL DATA	Characteristics	Standards	EXPONA LINNÉ
    <p>PHthalate FREE</p>    	<b>Type of floorcovering</b>	EN 649	heterogeneous, PVC
	<b>Surface treatment</b>		
	<b>Performance classification</b>	EN 685	23   34   43
	<b>Gauge</b>	EN 428	3.0mm
	<b>Wear layer thickness</b>	EN 429	0.7mm
	<b>Packaging tile sizes</b>	EN 427	16 @ 457mm x 457mm = 3.34m <sup>2</sup>
	<b>Residual indentation</b>	EN 433	pass
	<b>Colour fastness to artificial light</b>	EN ISO 105-B02	level 6 ≥ method A
	<b>Behaviour to fire</b>	EN 13501-1	B <sub>fl</sub> - s1
	<b>Slip resistance</b>	DIN 51130 EN 13893	R10 DS
	<b>Sound reduction</b>	EN 140-8 EN ISO 10140-3	3 dB
	<b>Chemical resistance</b>	EN 423	*
	<b>Abrasion group</b>	EN 660-2 EN ISO 10582	T Typ 1
<b>Castor chair suitability</b>	EN 425	yes   type W   EN 12 529	
<b>Underfloor heating suitability</b>	EN 1264-2	suitable   max. 27° C	

\*Resistance depending on concentration and time of exposure, in case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals - please contact Polyflor.