

Polyflor Booster Collection

Domestic Cushion Vinyl



Boston Pecan 1722



Chelsea Smoked 1294



City light Grey 1206



Hudson Blond 1887



Hudson Pearl 1880



Madras Silver 1593



Nordic Beige 1689



Patio Silver Grey 1958



Quartzite Sand 1946



Spa Silver Grey 1919



Hudson Pearl 1880

Polyflor Booster Collection

Domestic Cushion Vinyl



TECHNICAL CHARACTERISTICS

Booster

Total thickness	EN 428	mm	2.60
Thickness of the wear-layer	EN 429	mm	0.25
Weight / Mass per unit area	EN 430	g/sqm	1725
Width of sheet	EN 426	m	2 / 3 / 4
Length of sheet	EN 426	ml	± 30
Surface treatment	-	-	TopFinish
Norm / Product specification	-	-	EN 653
European classification	EN 685	class	23/31
Fire rating - Classification	EN 13501-1	class	C _f -s1
Wear group	EN 653	group	T
TVOC rate 28 days	-	µg/m ³	< 100
VOC rate (French norm)	-	-	A+
Impact sound insulation	EN ISO 717/2	dB	19
Room impact noise	NF S 31074	class	A
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10
Dimensional stability after exposure to heat	EN 434	%	0.05
Residual indentation	EN 433	mm	0.15
Thermal conductivity	EN 12 524	W/(m.k)	0.25
Colour fastness	EN 20 105-B02	degree	> 6
Wet rooms	-	-	OK
Floor heating	-	-	OK - T < 28°C
Static electrical probersity	NF EN 1815	kV	≤ 2
Guarantee		year	10

CE MARKING



EN 14041



Areas of use: domestic use

